

Self Leveling Products

Terminology

- Underlayment
- Overlayment
- Priming



In 25 kg bags

Product	Recommended Thickness (mm)	Foot Traffic Allowed (hr)	Flow (mm)	Compressive Strength	Substrate Build Up
Flowment 550	3 – 30	2 – 4	150	30 MPa	New and old concrete
Flowment Rapid 560	2 – 20	2	160	30 MPa	New and old concrete, plywood or Gypsum boards
Flowvinyl 565	2 – 20	2	160	30 MPa	New and old concrete
Flowtop 860	4 – 15	1 – 3	160	30 MPa	Concrete of good quality
Floorprime	0.15 – 0.40 kg/m ²	-	-	-	Concrete, stone, ceramics, timber, etc